

REC'D 1 0 MAR 2005

WIPO

PCT

HICKORIUBD STATES DRAY OF TON

TO ALL TO WHOM THUSE; PRESENTS SHALL, COMES
UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 04, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/556,194

FILING DATE: March 25, 2004

PRIORITY DOCUMENT
PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN

COMPLIANCE WITH

COMPLIANCE OR (b)

RULE 17.1(a) OR (b)

By Authority of the

COMMISSIONER OF PATENTS AND TRADEMARKS

LANAI JAMISON

Certifying Officer

PTO/SB/16 (08-03)

Approved for use through 07/31/2006. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53 (c). Express Mail Label No. EV146 601 392US Date of Deposit: March 25, 2004

		IN	VENTOR(S)			•	
Given Name (first and middle [if any])		Family Name or Surname		ne (City an	Residence (City and either State or Foreign Country)		
Paul David		Kemp		10.07.00	Romiley, United Kingdom		
Michael John			McWhan	1	erbyshire, Unite	_	
Additional inventors are being	ng named on th	e Page 2 of			 -	0	
			ENTION (500 cl				
PACKAGING FOR A WOUND	HEALING COM	//POSITION				L.S.	
Direct all correspondence to:	CORRES	PONDEN	CE ADDRESS			<u>ي</u>	
	34139)	·			22581 60/51	
OR						255	
Firm <i>or</i> Individual Name							
Address							
Address			T	<u></u>	· · · · · · · · · · · · · · · · · · ·		
City			State		. ZIP		
Country	ENCLOSED	ADDITION	Telephone	l	Fax		
		APPLICA	IUN PARTS (CI	neck all that app			
Specification <i>Numbe</i>	er of Pages	<u>25</u>	Ĺ	CD(s), Num	ber		
☑ Drawing(s) <i>Number</i>	of Sheets	<u>02</u>	\triangleright	\subseteq Other (specif	y): <u>Fee Trans</u>	mittal for FY	
Application Data She	eet. See 37 Cl	FR 1.76	20	004			
METHOD OF PAYMENT OF FILING	FEES FOR THIS	S PROVISIO	NAL APPLICATION	N FOR PATENT		· · · · · · · · · · · · · · · · · · ·	
Applicant claims small e	entity status	See 37 CF	R 1 27				
A check or money orde						FILING FEE	
			_			AMOUNT (\$)	
The Director is hereby		-					
fees or credit any overp Payment by credit card	-	•		<u>50-1275</u>	•	\$80.00	
The invention was made by the United States Government	an agency of			nment or under	a contract with	n an agency of	
⊠ No.							
Yes, the name of the U.S. G	Sovernment age	ency and the	<u></u>	ontract number ar	e:		
Respectfully submitted, SIGNATURE	enfal	hoes	Page 1 of 2]	Date 3/2 STRATION NO.	25/04 35,719		
TYPED or PRINTED NAME	Dorgen Yati	ko Trujillo	•	propriate)	73,		
TELEPHONE (215) 665-	5593		Dock	et Number:	HARR0036	-001	

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

PROVISIONAL APPLICATION COVER SHEET

Additional Page

PTO/SB/16 (08-03)

Approved for use through 07/31/2006. OMB 0851-0032

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Docket Number HARR0036-001 INVENTOR(S)/APPLICANT(S) .				
Given Name (first and middle [if any])	Family or Surname	Residence (City and either State or Foreign Country)		
Penelope Ann	Johnson	Derbyshire, United Kingdom		
Györgyi	Talas	Cheshire, United Kingdom		

Page 2 of 2

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

FE	ET	RA	NS	SMI	TT	AL
	fc	r F	Y	200	4	

Effective 10/01/2003. Patent fees are subject to annual revision.

Applicant claims small entity status. See 37 CFR 1.27

TOTAL AMOUNT OF PAYMENT

(\$)	80.00

	A CONTRACTOR OF THE CONTRACTOR		
Complete if Known			
Application Number	Not Yet Assigned		
Filing Date	March 25, 2004		
First Named Inventor	Paul D. Kemp et al.		
Examiner Name	Not Yet Assigned		
Art Unit	Not Yet Assigned		
Attorney Docket No.	HARR0036-001		

METHOD OF PAYMENT (check all that apply)					FEE C	ALCULATION (continued)	· · · · · · · · · · · · · · · · · · ·				
☐ Check ☐ Credit card ☐ Money ☐ Other ☐ None		3. AD	DITION	IAL FE	ES		· ·				
Order Deposit Account:		Large	Entity	Small E	ntity						
Depos	•					Fee Code	Fee (\$)	Fee Code	Fee (\$)	Fee Description	Fee Paid
Accou	ınt	50-1275			İ	1051	130	2051	65	Surcharge - late filing fee or oath	
Numb	er					1052	50	2052	25	Surcharge - late provisional filing fee or cover sheet.	
Deposit				1053	130	1053	130	Non-English specification			
Accou Name		Cozeл O'(Connor,	P.C.		1812	2,520	1812	2,520	For filing a request for reexamination	
The Direc	ctor is au	thorized t	o: (che	eck all that apply)		1804	920*	1804	920*	Requesting publication of SIR prior to Examiner action	
	e fee(s) ir e any add	ndicated be litional fee	elow [(s) duri	□ Credit any overpains the pendency of the pendency o	this application	1805	1,840*	1805	1,840*	Requesting publication of SIR after Examiner action	
to the abo	e iee(s) ir we-identii	idicated be fied deposi	elow, e	xcept for the filing	fee	1251	110	2251	55	Extension for reply within first month	
to the abo	ove-identi			CULATION		1252	420	2252	210	Extension for reply within second month	
1. B	ASIC FI	LING FE	E			1253	950	2253	475	Extension for reply within third month	
Large Ent	tity 5	Small Entity	Ł.			1254	1,480	2254	740	Extension for reply within fourth month	
	•	ee red ode (\$)		ee Description	Fee Paid	1255	2,010	2255	1,005	Extension for reply within fifth month	
	• • •	001 385		lility filing fee		1401	330	2401	165	Notice of Appeal	
1002	340 26	002 176		esign filing fee		1402	330	2402	165	Filing a brief in support of an appeal	
1003	530 20	003 265	5 PI	ant filing fee		1403	290	2403	145	Request for oral hearing	
		004 385 005 80	5 Re	elssue filing fee rovisional filling fee	80-00	1451	1,510	1451	1,510	Petition to institute a public use proceeding	
1005	100 20	<i>3</i> 03 00	<i>-</i> - 1	ovisional ming lee	80.00	1452	110	2452	55	Petition to revive unavoidable	
		SUBT	OTAL ((1)	(\$) 80.00	1453	1,330	2453	665	Petition to revive - unintentional	
60 FED 6 FED						1501	1,330	2501	665	Utility issue fee (or reissue)	
2. EXTR	RA CLAI	M FEES		UTILITY AND RE		1502	480	2502	240	Design issue fee	
				Extra Fee from Claims below	n Fee Paid	1503	640	2503	320	Plant issue fee	
Total Claims	s 00	- 20 **		00 X		1460	130	1460	130	Petitions to the Commissioner	
Independent		一				1807	50	1807	50	Processing fee under 37 CFR 1.17 (q)
Claims	00	- 03 **	= []	00 X	=	1806	180	1806	180	Submission of Information Disclosure Stmt	
Multiple Dependent Large Ent		Small E	in titur			8021	40	8021	40	Recording each patent assignment per property (times number of properties)	
Fee	Fee	Fee	Fee			1809	770	2809	385	properties) Filing a submission after final rejection	
Code 1202	(\$)	Code	(\$)	Fee Description	500					(37 CFR § 1.129(a))	
1202	18 86	2202 2201	9 43	Claims in excess o	•	1810	770	2810	385	For each additional invention to be examined (37 CFR § 1.129(b))	
1203	290	2201	43 145	Independent claim: Multiple dependent							
1204	86	2204	43	** Reissue indeper		1801 1802	770 900	2801 1802	385 900	Request for Continued Examination (RCE Request for expedited examination)
1205	18	2205	9		n excess of 20 and			1002		of a design application	
over original patent			Other fo	ee (specif	ý)	_					
SUBTOTAL (2) (\$)											
**or number previously paid, if greater; For Reissues, see above			*Redu	ced by Ba	isic Filin	g Fee Pa	aid SUBTOTAL (3) (\$)				
		, ,				<u></u>					

SUBMITTED BY Complete (if applicable) Registration No. Dorgen Yatko Trujillo Name (Print/Type) **39**,719 (Attorney/Agent) Telephone (215) 665-5593 Signature Date March 25, 2004

WARNING: Information on this form may become public. Credit card information should not be

included on this form. Provide credit card information and authorization on PTO-2038.

This collection of information is required by 37 CFR 1.17 and 1.27. The information is required to obtain or relain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 12 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing this form, call 1-800-PTO-9199 (1-800-786-9199) and select option 2.

PACKAGING FOR A WOUND HEALING COMPOSITION

· Field of the invention

5

10

15

20

25

30

The invention concerns compositions useful for assisting the process of wound healing, particularly chronic open lesions that are slow to heal. It conveniently delivers live cells with the capacity to initiate and encourage the healing process, in a biocompatible matrix.

Background to the invention

Healing of open wounds extending through the germinal epithelium in otherwise healthy tissue takes place by the process classically described as 'second intention', which, following initial haemostasis, involves a well-ordered sequence of inflammation, cellular infiltration, angiogenesis, granulation and re-epithelialisation. Where the wound has destroyed the germinal layer of the epithelium, collagen deposition by infiltrating fibroblasts and re-epithelialisation results in a degree of scarring, with incomplete restoration of function in terms of the flexibility and elasticity of the original dermis and failure to regenerate auxiliary structures such as hair follicles and sweat glands. Various approaches of autologous skingrafting have long been used to close open wounds, minimise the risk of opportunistic infection, accelerate healing and minimise scarring.

However, a number of factors may adversely affect the rate and extent of such wound healing, in particular, poor blood supply. Poorly perfused tissue, often associated with impaired venous return and varicose veins, peripheral vascular disease or diabetes, often fails to heal satisfactorily, resulting in chronic ulcers, although the details of the pathogenesis are still unclear.

Current methods of skin grafting have significant limitations, not least the requirement for a suitable donor site from which grafts can be taken, especially where wounds are extensive (for example, burns). In addition, grafts have a low success rate where wound healing is compromised.

Chronic leg ulcers are a significant and growing problem world-wide. The introduction of compression therapy in combination with moist wound dressings has been the standard therapeutic management. More recently, tissue-engineering solutions have become available. Research into regenerative medicine has shown that human cells have substantial potential to heal and regenerate damaged tissue especially when primed by an environment that closely mimics the natural physiological condition being treated.

10

15

20

25

30

35

Much of the research has focused on the production of so-called 'tissue equivalents', which aim to provide a temporary functional replacement for missing tissue and accelerate healing. Such tissue equivalents may be dermal equivalents or total skin equivalents, the aim being to provide effective coverage of the wound as quickly as possible. The development and production of tissue equivalents usually involves the isolation of replacement skin cells, which are expanded and seeded onto / into a supporting structure such as a three-dimensional bio-resorbable matrix, or within a gel-based scaffold.

A variety of materials have been used as acellular protein matrices for wound healing applications.

These include synthetic polyesters (polyglycolic acid (PGA), polylactic acid (PLA), polyglactide (DermagraftTM, Smith & Nephew, described below), polydioxanone, polyhydroxyalkonoates and hyaluronic acid derivatives), hydrophilic polyurethanes (polyetherpolyester, polyethylene oxide and carboxymethylcellulose ethylene), and collagen-based scaffolds (cross-linked elastin collagen material (MatridermTM), cross-linked collagens manufactured from acid-soluble type I bovine collagen material (such as VitaphoreTM). An alternative approach is to use an acellular derivative of allogeneic human dermis, a natural dermal matrix from which cells have been removed (such as Alloderm®, LifeCell Corporation). Some preparations use an organised, layered structure in order to more closely mimic the structure and function of the dermis. For instance, a preparation comprising an underlying layer of bovine collagen and shark glycosaminoglycans with an overlying layer of silicone is known (Integra®, Integra LifeSciences Corporation). Other approaches have involved utilising fibrin sealants. Fibrin sealants (such as Tisseel TM, Baxter; Beriplast TM, Aventis; Quixil TM, Omrix Biopharmaceuticals; Haemaseel TM, Haemacure; and Crosseal TM, Omrix) have been available for some time. All of these commercially available fibrin sealants are derived from cryoprecipitate from pooled plasma from virally screened allogeneic donors.

Such fibrin products rely on the natural polymerisation process that occurs during the physiological blood clotting cascade, in which a monomeric fibrin precursor, fibrinogen, is acted on by activated thrombin with the resultant production of polymeric fibrin. Fibrin forms the protein scaffold component of blood clots, to which platelets adhere.

More recently, fibrin has been recognised as a convenient and clinically acceptable cell carrier to be used in tissue engineering applications. Commercially available products that utilise fibrin sealants for cell delivery include BioseedTM (Biotissue technologies), although several research groups make reference to the use of fibrin sealants for cell delivery

purposes results of which have shown some promise in burns (Brown *et al.* (1993) Am J Pathol <u>142</u>: 273–283; Neidert *et al* (2001) 2001 Proceedings of the ASME Bioengineering Conference, Eds Kamm *et al*, Vol 50: 215–216; Tuan *et al* (1996) Exp Cell Res <u>223</u>: 127–134; and US Patent application 200301654482)).

5

10

15

20

25

30

35

Exogenously applied dermal cells have been consistently shown to have beneficial effects on wound healing including shorter time to complete healing (Falanga and Sabolinski (1999) Wound Repair Regen 7: 210–207); delivery of active growth factors to the wound (Naughton et al. (1997) Artif Organs 21: 1203–1210); reduced potential for lesion recurrence (Gentzkow et al (1996) Diabetes Care 19: 350–354; and reduced pain (Muhart et al (1999) Arch Dermatol 135: 913–918).

As part of the normal healing response resident fibroblasts are required to undergo a series of phenotypic changes, migrating to the wound site, then proliferating, then synthesising and secreting extracellular matrix molecules. In vivo, a least a proportion then switch to a myofibroblastic phenotype in order to facilitate wound contraction (Clark (1993) Am J Med Sci 306: 42-48). In vitro, a series of phenotypically distinguishable mitotic and post-mitotic fibroblast populations have been described (Bayreuther et al (1988) Proc Natl Acad Sci USA 85: 5112-5116). This differentiation pathway appears to be controlled, at least in part, by interactions between fibroblasts and extracellular matrix (ECM) proteins present at the wound site. Growth factors and cytokines undoubtedly also exert an important influence, although their effects too, appear to be modulated by fibroblast exposure to particular ECM proteins (Eckes et al (1999) Springer Semin Immunopathol 21: 415-429; Xu and Clark (1996) J Cell Biol 132: 239-249). Among the ECM proteins that appear to have an important role in fibroblast differentiation are fibrinogen and fibrin. Fibroblasts specifically interact with fibrin and fibrinogen RGD motifs through $\alpha_v\beta_3$ integrin receptors (Gailit et al (1997) Exp Cell Res 232: 118-126) although the cellular response is complex and modulated by other factors. In vitro studies of the effect of fibrin glue on human periodontal ligament fibroblasts have suggested that fibrin appeared to slightly inhibit fibroblast proliferation (Fabris et al (1998) J Clin Periodontol 25: 11-14). The presence of a fibrin matrix has also been reported to increase the synthesis of collagen by entrapped fibroblasts (Neidert et al, 2001) The interaction between fibroblasts and ECM, in particular fibrin, and its influence on the activation and/or differentiation of fibroblasts is clearly of relevance when considering wound healing compositions comprising fibrin and live fibroblasts and attempting to optimise their therapeutic effects.

10

15

20

25

30

35

Fibroblasts also have a role in the remodelling of fibrin clots. As new extracellular matrix proteins such as collagen type I and III, fibronectin and vitronectin are laid down, the fibrin matrix is broken down, predominantly by the activation of the plasma-derived enzyme plasmin. This is regulated by the activation (or inhibition) of its proenzyme, plasminogen, by a variety of plasminogen activators and inhibitors. *In vivo*, a number of infiltrating cells, such as neutrophils and macrophages, secrete urokinase-type plasminogen activator (uPA), whilst endothelial cells are largely responsible for producing tissue plasminogen activator (tPA). However, it also clear that fibroblasts also secrete both uPA and plasminogen activator inhibitors, such as plasminogen activator inhibitor-1 (PA-1). The balance between these antagonistic mediators is crucial in controlling fibrin remodelling and scar formation (Tuan *et al*, 2003, Am J Pathol <u>162</u>: 1579–1589). It is also clear that their expression is developmentally regulated, as well as being controlled by extracellular matrix components and local growth factors (Island *et al*, 1999, Wound Repair Regen <u>7</u>: 467–476).

To facilitate movement through the cross-linked fibrin clot and a tight meshwork of extracellular matrix, a variety of fibroblast- and serum-derived enzymes cleave a path for migration. These include interstitial collagenase (matrix metalloproteinase-1, MMP-1), gelatinase (matrix metalloproteinase-2, MMP-2), stromelysin (matrix metalloproteinase-3, MMP-3) and the plasminogen activators (Grant GA, Eisen AZ, Marmer BL, Roswit WT, Goldberg GI (1987) J Biol Chem, 262: 5886-5889; Wilhelm SM, Collier IE, Kronberger A, Eisen AZ, Marmer BL, Grant BA, Bauer EA, and Goldberg GI (1987) Proc Natl Acad Sci USA, 84: 6725-6729; Stetler-Stevenson WG, Krutzsch HC, Wacher MP, Marguiles IMK, Liotta LA (1989) J Biol Chem, 264:1353-1356). Additionally, chemotactic factors, such as TGF-β and PDGF may also upregulate their production and secretion (Laiho M, Saksela O, Keski-Oja J (1986) Exp Cell Res, 164:399-407; Overall CM, Wrana JI and Sodek J (1989) J Biol Chem, 264: 1860-1869.).

Once migrating fibroblasts reached the wound, they gradually become secretory, whose major function is protein synthesis (Welch MP, Odland GF, Clark RAF (1990) J Cell Biol, 110:133-145). The previously retracted endoplasmic reticulum and Golgi apparatus becomes dispersed throughout the cytoplasm and a loose matrix is produced, which is mainly composed of fibronectin and type III collagen (Kurkinen M, Vaheri A, Roberts PJ, Stenman S (1980) Lab Invest, 43: 47-51; Grinnell F, Billingham RE, Burgess L (1981) 76:181-189). Ultimately, this profibrotic phenotype takes over, which is characterised by an abundance of rough endoplasmic reticulum and golgi apparatus, secreting newly synthesised collagen (Welch *et al.*, 1990) in response to highly expressed TGF-β.

Notwithstanding, TGF-β fails to upregulate further collagen deposition, once a matrix has been deposited (Clark RAF, Nielsen LD, Welch MP, McPherson JM (1995) J Cell Sci, 108: 1251-1261). It is also thought that IL-4 released by mast cells induces a modest increase in types I and III collagen together with fibronectin (Postlethwaite AE, Holness MA, Katai H, Raghow R (1992) J Clin Invest, 90:1479-1485). Mast cells furthermore produce tryptase (a serine esterase) in abundance, which has been shown to upregulate fibroblast proliferation (Ruoss SJ, Hartmann T, Caughey GH (1991) Clin Invest, 88: 493-499).

The stimuli responsible for fibroblast proliferation and matrix synthesis (TGF-α, TGF-β and PDGF) have been extensively investigated *in vitro* (Derynck R (1988) Cell, 54: 593-595; Ross RR and Raines EW (1990), Platelet-derived growth factor and cell proliferation, in: Growth Factors: From genes to clinical applications (VR Sara et al. eds.,) pp. 193-199, Raven Press, New York; Sporn MB and Roberts AM (1992) J Cell Biol, 119:1017-102) and their action was confirmed by *in vivo* manipulation of wounds as well (Sprugel KH, McPherson JM, Clowes AW, Ross R (1987) Am J Pathol, 129: 601-613; Pierce GF, Mustoe

- McPherson JM, Clowes AW, Ross R (1987) Am J Pathol, 129: 601-613; Pierce GF, Mustoe TA, Altrock B, Deuel TF and Thomas A (1991), Role of platelet-derived growth factor in wound healing, J Cell Biochem, 45:319-326). γ-interferon on the other hand was demonstrated to have a negative effect on the mitogenic and synthetic potential of fibroblasts *in vitro* and *in vivo* (Duncan MR and Berman B (1985) J Exp Med, 162: 516-527;
- Granstein RD, Murphy GF, Margolis RJ, Byrne MH and Amento EP (1987) J Clin Invest, 79: 1254-1258). In addition, the collagen matrix itself can suppress these activities (Grinnell, 1994; Clark et al., 1995), whilst fibrin or fibronectin matrix has little or no suppressive effect (Clark et al., 1995).
- Interestingly, many fibroblasts undergo apoptosis (programmed cell death) in day-10 healing wounds (Williams GT (1991) Cell, 65: 1097-1098), thereby marking the transition from a fibroblast-rich granulation tissue to a scar tissue with reduced cell density.
- Known combinations of protein matrices and live cells for wound healing applications may be summarised as follows.

A preparation comprising cryo-preserved primary human foreskin fibroblasts seeded onto a bioabsorbable glycolic-lactic acid polyester (polyglactide) scaffold (DermagraftTM, Smith & Nephew) is known for the treatment of ulcers (Naughton *et al*, 1997, US patent nos.

4,963,489,). The fibroblasts are allowed to proliferate in the scaffold, secreting extracellular matrix proteins and growth factors and cytokines. The mature preparation is packaged in

10

15

30

35

10% dimethylsulphoxide and bovine serum as a cryoprotectant to allow storage of the product by freezing prior to use. The disadvantages of this approach include difficulty in manipulating the product during application to the wound, and the necessity of storing and transporting the product at very low temperatures (-70°C) and use of careful thawing procedures in order to ensure viability of the cells (WO 87/06120).

Various combinations of collagen-based matrices and living cells are known. Apligraf® (Organogenesis Inc), is a bilayered structure comprising a lower ('dermal') layer of a bovine collagen scaffold supporting living human fibroblasts and a upper ('epidermal') layer comprising human keratinocytes on a collagen scaffold (Falanga and Sabolinski,1999, WO 99/63051). The preparation is supplied as a circular disk approximately 75 mm in diameter and 0.75 mm thick on an inert polycarbonate membrane. It is packaged individually for use and has 5-day shelf life. It is maintained in an agarose rich nutrient with a 10% CO₂/ air atmosphere and is shipped and stored at room temperature (20°C to 31°C; 68°F to 88°F). The removal of the product form the storage dish and polycarbonate membrane is involves teasing away the edge of the Apligraf using sterile forceps. Problems associated with this include excessive folding which can make accurate, close application of the preparation to the wound difficult and time consuming.

A similar product (OrcelTM, Ortec International Inc) is described in US patent 6,039,760. This is also a bilayered structure of bovine collagen with fibroblasts and keratinocytes. The preparation is packaged between 2 non-adherent pieces of mesh, which are colour coordinated to distinguish between sides. The device is then packaged in a plastic tray containing media to maintain cell viability during storage and shipping, which is further packaged into pouches with chill packs to maintain a temperature of 11-19°C for 72 hours.

Other examples of tissue equivalents that attempted to reproduce a dermis-like arrangement of fibroblasts in a protein matrix supporting an overlying layer of keratinocytes are described in Meana *et al* (1998, Burns <u>24</u>: 621–630).

Rama et al (2001, Transplantation 72: 1478–1485) describe a method of culturing autologous limbal stem cells on a fibrin gel substrate for grafting to the contralateral cornea.

US Patent application 20030165482 discloses a wound healing preparation (Allox[™], Modex Therapeutiques SA) comprising growth-arrested allogeneic human fibroblasts applied to a wound in a viscous paste of fibrinogen (Tisseel[®]) to which thrombin has been added, so that

fibrinogen cleavage and fibrin polymerisation occur in situ. Alternatively, the separate liquid components are sprayed onto the wound, to set in situ, on mixing.

Summary of the invention

5

10

15

20

25

30

35

The invention provides an approach to treatment of chronic wounds based, not on providing an immediately functional tissue-equivalent, but on providing a means of delivering cells with the potential to accelerate the healing process together with a supportive, biologicallycompatible protein matrix. Although developing a cultured dermal tissue equivalent comprising fibroblasts, extracellular matrix and overlying keratinocytes organised in to functional and anatomically relevant structures remains a worthwhile goal, so far this has proven elusive. However, for many situations, the present invention shows that such an approach may be unnecessarily complex and that a simpler solution, that of providing fibroblasts at the appropriate stage of maturity and exhibiting a particular phenotype embedded at appropriate cell densities in a fibrin (or other clottable protein) matrix, in a wound-healing composition for rapid, convenient and accurate application to wounds, is surprisingly effective. Although fibrin is a convenient and physiological extracellular matrix protein for use in a cell delivery product, the complex interaction between fibrin and fibroblasts also has important implications for ensuring that cells delivered to the wound surface have optimal wound healing potential. Optimally the cells must be in a synthetic phase of maturity, rather than a proliferative or senescent phase. Proliferation maybe useful to increase cell numbers, but delays the important synthesis of extracellular matrix proteins such as collagen types I and III, fibronectin and vitronectin. Cells that have become senescent do not contribute to wound healing and so serve little purpose in such a composition. An important aspect of the invention, therefore is use of young fibroblasts with a 'wound-healing phenotype (a phenotype that is either actively synthetic, or that can rapidly mature to such a phenotype), to encourage immediate wound healing, and the delivery of such cells to a wound in a matrix that is consistent with the maintenance of such a phenotype. Fibrin is such a matrix material, although other materials, such as agar, alginate, and polyvinyl alcohol (PVA) are also suitable.

Another important factor is the rate of fibrinolysis occurring within the composition. As described above, fibrinolysis is a normal part of the wound healing process, by which the fibrin matrix is gradually replaced by other extracellular matrix proteins. If, however, fibrinolysis occurs too early or too rapidly, the wound healing gel is broken down before useful collagen deposition has occurred. Fibroblast expression of pro-fibrinolytic factors

such as urokinase-type plasminogen activator is developmentally regulated and so the phenotype of fibroblasts included in the composition is of importance if premature fibrinolysis is to be avoided.

The fibroblast phenotype is therefore important to optimal wound healing. Human dermal fibroblasts in wound healing compositions in which they are embedded in collagen or in mature skin products have a different phenotype (for instance collagen gene expression will be very low as will fibrin and thrombin response genes). Preferably early gene expression will include elevated collagen gene expression and other genes involved in the early exposure of fibroblasts to a wound environment

Generating a gene expression profile allowing identification of appropriate early fibroblast phenotypes includes use of three different methods.

- Quantitative PCR (TaqMan) is used to measure the amounts of particular genes being expressed by fibroblasts. The genes to be screened include: Gas6 (growth arrest-specific 6, also known as AXSF or AXLLG), collagen types I, III, and VI, PAI-1 (plasminogen activator inhibitor type-1), INSIG-1 (Insulin-induced gene 1), PLAU (plasminogen activator, urokinase), Collagen type VI, COX-2 (cyclo-oxygenase-2),
 PDGF (platelet-derived growth factor), vimentin, smooth muscle actin, apolipoprotein D, MMP-2 (matrix metalloprotease 2, gelatinase), GAPDH (glyceraldehyde-3-phosphate dehydrogenase), and RPL32 (ribosomal protein L32). Other informative genes include those encoding cytokines, metabolic genes, cytoskeletal genes, cell surface molecules and cell signalling molecules.
 - 2. Differential display is a PCR-based method using non-specific primers, which produces a banding pattern when run on a gel that is unique to the sample of interest. This results in a "barcode" type pattern of gene expression. The advantage of this process is that it is fairly quick to perform and produces an easily recognisable pattern that is can be read off without numerical manipulation, or knowledge of the actual genes involved.
 - 3. Microarray is a powerful technique for looking at global gene expression patterns. The advantage of this technique is that it looks at the gene expression of a large sample (~20,000) genes expressed by human cells. Therefore it is likely to capture all relevant genes.

30

35

10

15

20

25

30

35

It has been found that taking passaged human dermal fibroblasts, seeding them in a fibrin gel and then incubating them for 16-24 hours at 37° results in a phenotype that is particularly beneficial for use in wound healing applications. It has been observed that such cells are predominantly in a proliferative phase in culture (encouraged by low density seeding, avoiding contact inhibition). Under normal culture conditions, maturation to a wound-healing phenotype typically takes 2-3 days. However, incubation of fibroblasts in a fibrin gel shortens this maturation process, so that after 16-24 hours the cells are entering a wound-healing phenotype. Moreover, once they have reached this phase, they can preferably conveniently be stored at approximately 4°C for up to 19 days, and certainly 7-14 days before use without significant loss of viability or change of phenotype. This has significant practical advantages in that it provides not only an efficacious product comprising cells that are optimally suited for secretion of extracellular matrix with minimal inappropriate fibrinolysis, but also gives a relatively long shelf-life under commonly available standard refrigeration conditions. The ability to ship such products at approximately 4°C also considerably simplifies transportation. Maintaining a cold chain at 2°-8°C is considerably simpler and cheaper than shipping at -70°C, as is commonly required for live cells.

The product of the invention comprises a pre-cast fibrin gel in which passaged human dermal fibroblasts are seeded. The optimal ranges of cell density are believed to be from about 450 to about 2500 cells per mm², as measured per unit area of the cast gel. Within this range of cell densities, particular products have been developed using approximately 500 cells per mm² and approximately 1500 cells per mm².

One exemplary product uses a proprietary fibrin tissue sealant as described below in more detail in Example 1.

In a first aspect, the invention provides a package for a solid, or semi-solid, sterile, topical medicament comprising a flexible pouch consisting of two sheets of impermeable flexible material peripherally sealed to provide a means of containment, said pouch comprising one internal surface to which said medicament is preferentially adherent but to which the level of adhesion is less than that between the medicament and the bodily surface to be treated, such that the pouch may opened by parting said sheets and the medicament conveniently manipulated and directly to the surface to be treated without any requirement for the medicament to be directly touched by any other means before application. Preferably, the medicament comprises a wound healing composition comprising living cells, more preferably living mammalian cells within a sterile, non-pyrogenic fibrin matrix and most preferably the cells are human fibroblasts.

10

15

20

25

30

35

It is clear that such a package provides a convenient means of storage, delivery and application of any form of solid or, especially, semi-solid, materials, especially those intended for topical application to bodily surfaces. Such materials include cosmetics, beauty products or pharmaceuticals. Preferably such materials are of a semi-solid or gel nature, such that physical manipulation is difficult. The preferential adherence of the material to an element of the packaging, with the ease of transfer thereafter to the skin or other bodily surface, provides a considerable advantage. In particular, such materials may be cut to the required size before application to the intended area. In the case of wound healing compositions as herein described, this is particular advantage.

In a preferred embodiment, the package comprises coated or uncoated metal foil, laminated or metalised plastic. In one preferred embodiment it comprises a transparent area allowing visual inspection of its contents.

Preferably, the internal surfaces of the package and its contents are sterile.

In a preferred embodiment one internal surface of the pouch is modified to increase the adherence of the medicament thereto. In one embodiment this comprises application of a coating to one internal surface. Preferably the coating is selected from the list consisting of: a polymer, a thermoplastic, a thermo-setting plastic, a protein, an amino acid, a carbohydrate.

Alternatively, one internal surface is modified by roughening to increase the adherence of the medicament thereto. As used herein, 'roughening' includes any physical modification of the surface intended to improve adherence, such as embossing, scratching, abrading or scuffing, or chemical roughening by means of etching, erosion, acid or alkali treatment. Other means of modifying the surface energy properties of the surface in order to improve or modulate the degree of adherence of the solid or semi-solid product may be used. Such means include coating one internal surface of the pouch. Preferably such a coating is selected from the list consisting of a polymer, thermoplastic, thermo-setting plastic, protein, amino acid or carbohydrate.

In one particularly preferred embodiment, the internal surface is modified by means of a discontinuous coating, in the form of raised areas or dots, having the effect of providing a roughened surface.

Also provided is a method of packaging a sterile, solid or semi-solid topical medicament comprising: placing said medicament in a sterile flexible pouch consisting of two sheets of impermeable flexible material incompletely peripherally sealed to provide a means of partial containment, said pouch comprising one internal surface to which said medicament is preferentially adherent but to which the level of adhesion is less than that between the medicament and the bodily surface to be treated; and completely peripherally sealing said pouch to provide a means of containment.

Preferably, the medicament comprises a wound healing composition comprising living cells, more preferably living mammalian cells within a sterile, non-pyrogenic fibrin matrix. Most preferably, the cells are human fibroblasts. One internal surface of the pouch is preferably modified to increase the adherence of the medicament thereto, as herein described.

In another aspect the invention provides a method of treating a patient suffering from a skin lesion or other appropriate condition, comprising the topical application of a composition as herein described.

The method of treatment comprises applying a solid or semi-solid topical medicament by means of flexible pouch composed of two sheets of impermeable flexible material sealed to provide a means of containment and in which the medicament is preferentially adherent to the internal surface contributed by one of said sheets; comprising opening the pouch by parting the sealed sheets and manipulating the medicament whilst adherent to one of the sheets and applying the medication to the surface to be treated without any requirement for the medicament to be directly touched by any other means.

25 Preferably, the medicament is a wound healing composition comprises living cells, more preferably mammalian cells within a sterile, non-pyrogenic fibrin matrix. Most preferably, the cells are human fibroblasts.

Preferably the skin lesion to be treated is an ulcer or a burn, most preferably selected from the list consisting of venous ulcer, diabetic ulcer, pressure sore, burn, iatrogenic grafting wound.

In another aspect, the invention provides a means of storing and transporting a medicament comprising live mammalian cells at 2°–8°C.

In a further aspect, the invention provides a wound healing composition comprising living mammalian cells within a biological protein matrix characterised in that said matrix is pre-

35

30

5

10

15

20

cast before topical application. Preferably said matrix comprises fibrin. Alternatively it may comprise an alternative clottable or gelling substance such as agar, alginate or polyvinyl alcohol (PVA). Alternative suitable proteins include collagen, fibronectin and vitronectin.

- Preferably said wound healing composition comprises living mammalian cells within a sterile, non-pyrogenic fibrin matrix characterised in that said fibrin matrix is pre-cast before topical application.
- In a preferred embodiment said composition takes the form of a solid or semi-solid topical medicament. It is further preferred that the composition takes the form of a substantially disk-shaped cast gel, more preferably less than 8mm think, and most preferably less than 5mm thick.
- In a preferred embodiment said cells are fibroblasts. Alternatively, they may be keratinocytes, stratum germinativum cells, or combinations or admixtures of such cells. More preferably, said fibroblasts are human dermal fibroblasts.
 - Preferably, the composition contains 450 to 2500 cells per mm².
- In one aspect the invention provides a composition containing 500 to 1500 cells per mm², preferably 450 to 550 cells per mm².
 - In an alternative aspect, the composition contains 750 to 2000 cells per mm², preferably 900 to 1700 cells per mm², most preferably 1450 to 1550 cells per mm²
 - Preferably the concentration of fibrin is in the range 3-12mg ml⁻¹.

25

35

- In one alternative embodiment, the concentration of fibrin is in the range 3–5mg ml⁻¹. In a further alternative embodiment, the concentration of fibrin is in the range 5–20mg ml⁻¹, and is preferably in the range 7–12 mg ml⁻¹.
 - Also provided is method of manufacturing a wound healing composition, as described above, comprising: suspending living mammalian cells, in a solution comprising a protein monomer capable of polymerisation into an insoluble matrix, adding an agent capable of promoting such polymerisation and allowing polymerisation to occur in a mould such that the solid polymerised composition may be removed and packaged ready for topical

10

15

35

administration to a patient. Preferably, said monomer is fibrinogen and said agent capable of promoting polymerisation is thrombin.

In a preferred embodiment, the method of the invention comprises use of a protease inhibitor, preferably, preferably a serine protease inhibitor, most preferably one selected from the list consisting of aprotinin, ε-aminocaproic acid, tranexamic acid.

Preferably, especially where the concentration of fibrin is in the range 7–12mg ml⁻¹, the protease inhibitor is aprotinin. Alternatively, especially where the concentration of fibrin is in the range 3–5mg ml⁻¹, the protease inhibitor is tranexamic acid.

In a further aspect, the invention provides the composition as herein described for use as a medicament, preferably for the treatment of a skin lesion, more preferably a skin lesion selected from the list consisting of venous ulcer, diabetic ulcer, pressure sore, burn, iatrogenic grafting wound.

Also provided is the use of a composition as herein described in the manufacture of a medicament to treat such a skin lesion and a process to manufacture a medicament for the treatment of such a skin lesion.

In a final aspect, the inventio provides a method of storing and transporting a medicament comprising live mammalian cells at 2°–8°C.

Detailed description of the invention

The invention will now be described in detail with reference to the figures, wherein:

Figure 1 summarises the process of manufacturing the wound healing composition.

Figure 2 shows the packaging, manipulation and application of the wound healing composition. A: shows the set gel preferentially adhering to the modified internal surface of one of the two metalised plastic sheets of which the pouch is comprised. B: shows the use of one of the sheets of the package to apply the gel of wound healing composition to skin.

Note that sheet may used to support the gel while both are cut to the appropriate shape and size. C: shows the wound healing composition in place.

The invention relates to wound healing composition consisting of a topically applied viable cells of regenerative potential supported by a gel containing a fibrin matrix. Human dermal fibroblasts of a synthetic phenotype are particularly suitable for this purpose, although for

10

15

20

25

30

some applications keratinocytes or a combination of fibroblasts and keratinocytes may be more suitable.

The process of manufacturing the product is summarised in Figure 1. In principle, the product comprises two components, which are added together in order to cast a gel. The first component comprises a solution of fibrinogen together with one or more protease inhibitors to prevent unwanted proteolysis by protease contaminants and premature matrix breakdown by cells during storage. In particular, contaminants may include the naturally fibrinolytic enzyme plasmin, or its precursor plasminogen. Serine protease inhibitors such as aprotinin, ε-aminocaproic acid, or its analogue tranexamic acid, are frequently used in order to inhibit plasmin or prevent its activation. Added to this fibrinogen solution is a suspension of living cells in a suitable medium or buffer solution. The second component comprises a solution of thrombin (an enzyme that naturally acts upon fibrinogen), calcium ions (a required cofactor), and a medium suitable for the culture of living cells. A further clotting factor, Factor XIII, is also activated by thrombin in the presence of calcium ions and can be present in the second component. Activated Factor XIII promotes polymerisation of monomeric fibrin (cleaved from fibrinogen by thrombin) into a three-dimensional protein insoluble scaffold. In order to cast the gel, these two components are combined and poured into a pre-coated suitable mould whilst still liquid. Although commonly circular, clearly the gels may be cast into any shape. For some applications, other shapes may be more suitable. In particular, essentially rectangular or elliptical gels may be more convenient for larger wounds.

Enzymatic cleavage of fibrinogen into fibrin monomers and polymerisation of these monomers results in setting of the liquid into a semi-solid gel in which living cells are suspended. For many applications, this gel is then maintained for a period of about 24 hours under suitable conditions for cell growth, division and secretion of extracellular matrix proteins, and other proteins such as growth factors. Following maturation, the cast gels are removed from the casting moulds and placed directly into sterile packages. A small amount of medium is added to each package to maintain the product during storage and shipping, and the packages are sealed. During storage and shipping the packages are maintained at a temperature of 2°–8°C.

The advantages of such a product over the currently available alternatives include the following.

The use of a fibrin sealant as a scaffold allows convenient topical delivery of cells to the wound. The pre-cast gel allows convenient and accurate application of regenerative cells to the wound surface with control of the distribution and density of cells applied. Manufacture

and shipping of other tissue equivalents takes approximately 3 weeks for the matrix alone, whereas the product of the invention may be manufactured in 10 days, or even as little as 2 days if sufficient growing cells are available.

These factors combine to give cost advantages, so that manufacture and production is more cost effective than other commercially available products.

As described below, the product of the invention also features a unique flat pack system (adhesive backing) ensuring maintenance of product during shipping and "ease of use" of final product.

The precast gels can be shipped and stored for approximately 7–11 days at 2-8°C, whereas other available products are either frozen or shipped at room temperature.

Example 1 High protein concentration product ('Protoderm 500' and '1500')

One embodiment is designed to optimise both rapid manufacturing of the product and rapid wound healing by containing cells and protein components at relatively high concentrations.

Matrix

5

In this embodiment the matrix protein is fibrin, derived from a commercial fibrinogen product kit, Tisseel® (Baxter). When reconstituted this provides a convenient two component system to which cells may be added. The key components of the matrix are summarised in Table 1. It should be noted that Tisseel® also contains Factor XIII, as well as plasmafibronectin and plasminogen.

25 **Table 1**

20

Component	Final concentration in cellularised scaffolds
Matrix protein (fibrinogen)	7.5 - 11.5 mg/ml
Aprotinin	300 K IU/ml
Thrombin	25 IU/ml
Calcium chloride	4 mM

As will be clear to one of appropriate skill in the art, the exact concentrations of these components are not critical. Fibrinogen may be used in concentrations of the approximate range 7–20mg ml⁻¹ for this application, thrombin in the range 5-50 IU/ml (in fact, trace levels of contaminating thrombin will eventually lead to fibrin formation and gel setting without

additional thrombin, but this is inconvenient and unpredictable), and calcium chloride in the range 2–20mM. Aprotinin is used to prevent unwanted fibrinolysis but, again, the exact concentration is not critical.

5 Cells

10

15

20

25

30

35

Human dermal fibroblasts were obtained by culture of cells derived from neonatal foreskin tissue. Under GMP conditions, fibroblastic cells were isolated by collagenase digestion and expanded by culture and serial passage according to routine laboratory practice to establish a master cell bank (MCB). The MCB was screened against a panel of human and animal-derived viruses, bacteria, mycoplasma and fungi, and for tumorigenicity by a GLP-accredited facility and determined to be free of contamination. Several working cell banks (WCB) were then established for manufacture of the product, rescreened and stocks of cells frozen according to standard procedures. For manufacture, cells are thawed, recovered, expanded for 7 days in culture, and resuspended in appropriate volumes and densities as required. The cells were used at passage 7. Although early passage cells are strongly preferred, the exact passage number is not critical. Preferably it less than 20, more preferably it is less than 15, most preferably less than 10.

It is also envisaged that for various patient-specific applications, autologous fibroblasts or other cells obtained from biopsies may be cultured and expanded for use.

The density of cells used in the product is expressed in terms of the number of cells per unit area of the cast gel, which is in the range 450–2500 cells mm⁻², more preferably 750–2000 cells mm⁻², further preferably 900–1700 cells mm⁻², and most preferably approximately 1500 cells mm⁻². In order to maximise the rate of healing, it may be desirable to use a cell density of approximately 1500 cells mm⁻². The cells are suspended in Liebovitz L-15 cell culture medium buffered and supplemented as shown in Table 2 before addition to the fibrinogen component. As will be clear to one of skill in the art, medium not intended for use in a CO₂-enriched atmosphere (commonly used in tissue culture incubators or sealed flasks) must be appropriately buffered by some other system. Such media, supplemented with, for instance, HEPES, are well-known in the art. Liebovitz L-15 medium relies on a phosphate buffering system. The medium was supplemented with sodium bicarbonate and dextrose, as shown.

For convenience and consistency a standard 'working cell suspension' of 1.5x10⁶ cells ml⁻¹ is generally prepared.

Preparation of fibrin sealant

As outlined in Figure 1 and summarised below, TisseelTM thrombin powder is reconstituted in a calcium chloride solution according to the manufacturer's directions.

Once dissolved, the Thrombin/CaCl₂ solution is further diluted with supplemented L-15 medium to obtain a 'Working Thrombin Solution' and refrigerated until further use for a minimum of 15 minutes. (Gels may also be manufactured with 'Working Thrombin Solution' at room temperature.) Freeze-dried fibrinogen is reconstituted with an aprotinin solution before being added to the working cell suspension in supplemented L-15 medium. Once reconstituted, the fibrinogen should be used within 4 hours, ideally within 1-2 hours.

10

5

Working thrombin solution (6.75 ml) contains:

Thrombin: 50IU/ml (or 337.5IU total)

Calcium chloride: 8umoles/ml (or 54 umoles total)

in supplemented L-15

15 (Total refers to the amount in 6.75mls)

Working fibrinogen and cell suspension mix (total volume 6.75ml):

Tisseel: 19mg/ml (or 128.25mg total)

Aprotinin: 600KIU/ml (or 4050KIU total)

20 Cells: 1.2x10⁶ cell/ml (8.1x10⁶ cells total for P-1500);

0.4x10⁶ cell/ml (2.7x10⁶ cells total for P-500)

In supplemented L-15

(Total refers to the amount in 6.75mls)

25

Table 2 Medium

Components	Function	Concentration per ml
L-15 medium	Nutrient delivery to the cellular component of the product. Maintains cell viability and structure of the gel.	N/A (base medium)
Sodium Bicarbonate	Required for cell viability	202.5ug
Dextrose	Nutrient	4.5mg
Adenine	Base required for cell viability	24.4ug
L-Glutamine	Amino acid for cell viability	0.29mg
Ethanolamine	Phospholipid for cell metabolism	6.2ug
O-phosphoryl- ethanolamine	Phospholipid for cell metabolism	14.12ug
Hydrocortisone	Steroid required for cell metabolism	0.4mg
Human Recombinant Insulin	Essential hormone	5ug
Selenious acid	Trace substrate for metabolism	6.78ng
3,3',5-Triiodo-L-thyronine	Hormone	1.35ng
apo-Transferrin, bovine	Cofactor for iron metabolism	5ug
Gamma Irradiated Foetal Bovine serum	Nutrients	2%v/v

Casting the gels

The working thrombin solution (6.75ml) and TisseelTM fibrinogen/cell suspension mixture (6.75ml) are combined by means of a Duplojet mixer unit and loaded into a suitable precoated casting container (conveniently a sterile Petri dish or similar) via a 16G needle or equivalent. It is necessary to pre-coat the casting dish with serum containing media or albumin to prevent the gel from adhering. The gel sets within a few minutes. The gel is then bathed in 20ml of medium (Table 2) and the casting dish covered with a lid. The set gel incubated at 37°C for 16–24 hours to allow maturation of the cells.

Packing and Storage

5

10

20

25

After maturation, the set gels are removed from their casting containers and placed into preirradiated, sterile foil pouches, stored within a sterile roto-seal bag. 10ml serum-free medium (as per Table 2, without the foetal bovine serum) is added to each pouch before sealing.

The shelf life of the sealed units is approximately 11 days at 4°C.

Example 2 Low protein concentration product

For certain applications, it is possible to use lower protein concentrations. The chief advantage of this is reduction of production costs, since serum-derived proteins and many protease inhibitors, such as aprotinin, are expensive. In a preferred embodiment, the concentration of fibrin in the set product is reduced to less than 7 mg ml⁻¹. In practice, 3.0–4.0 mg ml⁻¹ is found to be effective.

One important consideration is the effectiveness (as well as the cost) of aprotinin as the protease inhibitor in such 'low protein' products. In particular, *pro rata* dilution of commercial products results in aprotinin concentrations that are too low to be effective. A preferable solution is to use an alternative inhibitor, such as tranexamic acid. Not only is this a highly effective inhibitor of fibrinolysis, but has significant cost advantages.

Low protein concentration product:

Matrix

In this embodiment the matrix protein is fibrin, sourced from a commercial fibrin sealant, TisseelTM using tranexamic acid instead of aprotinin. The key components of the matrix are summarised in Table 3. It should be noted that the same matrix composition could also be achieved using another commercially available fibrin sealant, Quixil. However the addition of exogenous tranexamic acid should be reduced as it already contains this inhibitor.

30 **Table 3.**

Component	Final concentration in cellularised scaffolds
Matrix protein (fibrinogen)	3.5mg/ml
Tranexamic acid	10mg/ml
Thrombin	25IU/ml
Calcium chloride	4mM

Freeze-dried TisseelTM fibrinogen is reconstituted with supplemented L-15 medium solution before being added to the working cell suspension in supplemented L-15 medium. Once reconstituted, TisseelTM fibrinogen should be used within 4 hours, ideally within 1-2 hours.

TisseelTM thrombin powder is reconstituted in a calcium chloride solution according to the manufacturer's directions. Once dissolved, the thrombin/CaCl₂ solution is further diluted with supplemented L-15 medium containing tranexamic acid to obtain a working thrombin solution.

10

The cell density used is again in the range 450–2500 cells mm⁻². In order to minimise costs, it may be desirable to use a cell density of approximately 450–550 cells mm⁻². It should be noted, however, that protein concentration and cells density are independent variables. Lowering protein concentration is the major cost determinant, rather than cell density. However, being able to use fewer cells may have implications for the speed of production. In any case, high cell density / low protein concentration and low cell density / high protein concentration embodiments are envisaged and may be preferred in specific circumstances.

20

25

15

Example 3 Packaging, storage and delivery

A major factor contributing to the success of topical wound healing products is the ease of accurately applying them to the wound surface so that a close contact is established, without air bubbles or creases, under sterile operating conditions. Such products are, by their nature, fragile, and handling should be kept to a minimum. The product of the invention is packaged in such a way as to significantly assist and facilitate application. In addition, the product is shipped and stored chilled, rather than frozen, so that detailed thawing procedures are not required prior to use.

30

35

After setting and the 16–24 hour culture and maturation period, the individual gel discs are packaged by insertion into a flexible foil or metallised plastic pouch comprising two rectangular sheets, sealed along a substantial portion of three of their sides so as to form an open pocket. The inner surface of one of these sheets is modified so as to increase its adherence to the fibrin gel product. In a preferred embodiment the packaging used is an Oliver Products (Grand Rapids, Michigan USA) peelable foil pouch comprising one foil sheet and one sheet of laminated polyester/foil sheet with Q15 Adhesive dot pattern coating. Q15/48BF1 is a laminated lidding and pouching material for medical devices. The purpose

10

15

20

25

30

of this dot pattern adhesive coating is to improve the efficiency of the heat sealing process which is used to seal the edges of the sheets together. However, the adhesive and raised dot pattern prove highly effective in providing a surface to which the fibrin gel product preferentially adheres, as compared with the smooth, uncoated inner surface of the opposing sheet. It will be clear to one skilled in the art that other forms of coating and/or roughening of the surface of one of the internal surfaces of the pouch could be used to achieve the same effect. Similarly, any suitably durable, flexible, water and gas-impermeable sheet material might be used to manufacture such a pouch. All or part of the packaging might be transparent to allow visual inspection, for example, of the integrity of the gel or of the colour of a pH indicator dye in the cell culture medium, a small volume of which is inserted in the pouch, along with the product, before the pouch is sealed along its remaining open edge.

Thus sealed, the product has a shelf-life of at least 7–11 days, and preferably up to 19 days, at 2°–8°C.

For application, the pouch is peeled apart, under sterile conditions, leaving the fibrin gel product adhering to the treated inner surface of one of the sheets comprising the pouch. Using the sheet as a backing or means of support the gel is then applied to the surface of the wound, to which, in the absence of excessive exudation, it will preferentially adhere allowing it to be peeled away from the sheet. This means of application allows the gel to applied without wrinkling or incorporation of air bubbles, and with the minimum of manipulation. The edges of the product may be easily trimmed to fit the limits of the wound. Another advantage of delivering the product removeably adherent to the packaging in this way is that it allows the easy identification of the orientation of the product and facilitates oriented application. In the case of a homogenous wound-healing product, it is unimportant which way up the product is applied to the wound. However, where a multilayered product is involved, such as one with a fibroblast layer that is intended to be applied in contact with the wound surface and a keratinocyte layer that is intended to be oriented away from the wound surface, it may be difficult or impossible to establish the orientation of the product visually. Then the ability to deliver the product in such a way as makes incorrect application impossible without first removing the product from the packaging offers a significant advantage.

The foregoing examples are meant to illustrate the invention and do not limit it in any way.

One of skill in the art will recognize modifications within the spirit and scope of the invention as indicated in the claims.

All references cited herein are hereby incorporated by reference.

What we claim is:

5

10

30

- 1. Package for a solid, or semi-solid, sterile, topical medicament comprising a flexible pouch consisting of two sheets of impermeable flexible material peripherally sealed to provide a means of containment, said pouch comprising one internal surface to which said medicament is preferentially adherent but to which the level of adhesion is less than that between the medicament and the bodily surface to be treated, such that the pouch may opened by parting said sheets and the medicament conveniently manipulated and directly to the surface to be treated without any requirement for the medicament to be directly touched by any other means before application.
- 2. A package according to claim 1, wherein the medicament comprises a wound healing composition comprising living cells.
- 15 3. A package according to claim 2, wherein the wound healing composition comprises living mammalian cells within a sterile, non-pyrogenic fibrin matrix.
 - 4. A package according to claim 3, wherein the cells are human fibroblasts.
- 5. A package according to any of claims 1 to 4 comprising metal foil or metalised plastic.
 - 6. A package according to any of claims 1 to 5 wherein the package comprises a transparent area allowing visual inspection of its contents.
- 7. A package according to any of claims 1 to 6, wherein one internal surface has been modified to increase the adherence of the medicament thereto.
 - 8. A package according to claim 7 wherein the modification comprises application of a coating to one internal surface.
 - 9. A package according to claim 8 wherein the coating is selected from the list consisting of: a polymer, a thermoplastic, a thermo-setting plastic, a protein, an amino acid, a carbohydrate, and combinations thereof.
- 10. A package according to any of claims 1 to 9, wherein one internal surface has been modified by roughening to increase the adherence of the medicament thereto.

10 .

25

35

- 11. A package according to any of claims 7 to 10, wherein one internal surface is modified by means of applying a discontinuous coating providing a roughened surface.
- 12. A method of packaging a solid, or semi-solid, sterile, topical medicament comprising: placing said medicament in a sterile flexible pouch consisting of two sheets of impermeable flexible material incompletely peripherally sealed to provide a means of partial containment, said pouch comprising one internal surface to which said medicament is preferentially adherent but to which the level of adhesion is less than that between the medicament and the bodily surface to be treated; and completely peripherally sealing said pouch to provide a means of containment.
- 13. The method according to claim 12 wherein the medicament comprises a wound healing composition comprising living cells.
- 14. The method according to claim 13, wherein the wound healing composition comprises living mammalian cells within a sterile, non-pyrogenic fibrin matrix.
 - 15. The method according to claim 14, wherein the cells are human fibroblasts.
- 16. A method according to any of claims 12 to 15, wherein one internal surface of the pouch has been modified to increase the adherence of the medicament thereto.
 - 17. A method according to claim 16, wherein the modification comprises application of a coating to one internal surface.
 - 18. A method according to claim 17, wherein the coating is selected from the list consisting of: a polymer, a thermoplastic, a thermo-setting plastic, a protein, an amino acid, a carbohydrate, and combinations thereof.
- 30 19. A method according to any of claims 16 to 18, wherein one internal surface has been modified by roughening to increase the adherence of the medicament thereto.
 - 20. A package according to any of claims 16 to 19, wherein one internal surface is modified by means of applying a discontinuous coating providing a roughened surface.
 - 21. A method of treatment comprising applying a solid or semi-solid, sterile, topical medicament by means of flexible pouch composed of two sheets of impermeable flexible

10

15

25

material sealed to provide a means of containment and in which the medicament is preferentially adherent to the internal surface contributed by one of said sheets; comprising opening the pouch by parting the sealed sheets and manipulating the medicament whilst adherent to one of the sheets and applying the medication to the surface to be treated without any requirement for the medicament to be directly touched by any other means.

- 22. The method according to claim 21 wherein the medicament is a wound healing composition comprising living cells.
- 23. The method according to claim 22, wherein the wound healing composition comprises living mammalian cells within a sterile, non-pyrogenic fibrin matrix.
- 24. The method according to claim 23, wherein the cells are human fibroblasts.
- 25. A method of treatment according to any of claims 21 to 24, wherein one internal surface of the pouch has been modified by applying a coating to increase the adherence of the medicament thereto.
- 26. A method according to claim 25 wherein the modification comprises application of a coating to one internal surface.
 - 27. A method according to claim 26 wherein the coating is selected from the list consisting of: a polymer, a thermoplastic, a thermo-setting plastic, a protein, an amino acid, a carbohydrate, and combinations thereof.
 - 28. A method according to any of claims 25 to 27, wherein one internal surface has been modified by roughening to increase the adherence of the medicament thereto.
- 30 29. A package according to any of claims 25 to 28, wherein one internal surface is modified by means of applying a discontinuous coating providing a roughened surface.
 - 30. A method of treating a skin lesion according to any of claims 21 to 29.
- 35 31. A method according to claim 30 wherein the skin lesion is an ulcer or a burn.
 - 32. A method of storing and transporting a medicament comprising live mammalian cells at 2°-8°C.

Sheet 1 of 2

Application Serial No.: Not Yet Assigned


Title: PACKAGING FOR A WOUND HEALING COMPOSITION Inventors: Paul D. Kemp, Michael J. McWhan, Penelope A. Johnson and

Györgyi Talas

Docket No.: HARR0036-001 Atty: Doreen Yatko Trujillo

Filed: March 25, 2004 Tel. No. (215) 665-5593

Figure 1




Application Serial No.: Not Yet Assigned
Title: PACKAGING FOR A WOUND HEALING COMPOSITION
Inventors: Paul D. Kemp, Michael J. McWhan, Penelope A. Johnson and Györgyi


Talas

Docket No.: HARR0036-001 Atty: Doreen Yatko Trujillo

Filed: March 25, 2004 Tel. No. (215) 665-5593

Figure 2







BEST AVAILABLE COPY